## **Display Graphics**

Gloss Topcoated White Vinyl Sheet for Rough Textured Surfaces - HP Indigo Compatible

Clear and white pressure-sensitive materials for point-of-purchase displays, menu boards and general purpose signage offer a permanent or removable bond for a variety of smooth, concave and textured surfaces.

End-Use Applications: Retail P-O-P Tradeshow General-Purpose Signage Menu Boards

For more information on FLEXcon's pressure-sensitive film solutions for Display Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX019537



Product:

## Flexcon® DigiPro® DGFWSRTS

## Benefits:

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Topcoat is specifically designed for digital printing with HP Indigo inks and ensures excellent ink receptivity for sharp vibrant image quality
- Acrylic adhesive offers high initial tack and high ultimate bond to a wide variety of rough textured surfaces, including low surface energy plastics and painted metal
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting
- Varnishing or overlaminating is recommended to protect graphics from abrasion

Please note: this product can also be used for durable applications. Contact your Technical Service Representative for more information.



## Flexcon® DigiPro® DGFWSRTS

| PRODUCT DATA                       | VALUE   |                             | TEST METHOD  |
|------------------------------------|---|-----------------------------|--|
| Physical Properties                |   |                             |  |
| Thickness (Mils[microns])          | Film  | 3.5 (89) +/- 10%            | ASTM D 3652 (Modified for use with                                     |
|                                    | Adhesive  | 1.9-2.1 (48-53) +/- 0.1 (3) | non-tape products)   |
|                                    | Liner   | 6.9 (175) +/- 10%           |  |
| Dimensional Stability (%)          | MD  | 0.75                        | Applied Shrinkage: 24 hour dwell                                       |
|                                    | TD  | 0.50                        | time on aluminum panel then 24 hours at 160°F (71°C)                   |
| Adhesion Properties                |   |                             |  |
| Ultimate Peel from                 | Average   |                             | ASTM D 903 (Modified for 72 hour                                       |
|                                    | Oz/In   | (N/m)                       | dwell time)  |
| ABS                                | 84  | (924)                       |  |
| ABS Textured Side                  | 40  | (440)                       |  |
| Acrylic                            | 130   | (1430)                      |  |
| Acrylic Powder Paint               | 83  | (913)                       |  |
| Aluminum                           | 91  | (1001)                      |  |
| Epoxy Powder Paint                 | 96  | (1056)                      |  |
| HDPE                               | 54  | (594)                       |  |
| Heavy Textured Aluminum            | 20  | (220)                       |  |
| Light Textured Stainless Steel     | 107   | (1177)                      |  |
| Painted Metal                      | 74  | (814)                       |  |
| Polycarbonate                      | 82  | (902)                       |  |
| Polyester                          | 89  | (979)                       |  |
| Polyester Powder Paint             | 79  | (869)                       |  |
| Polyurethane Powder Paint          | 91  | (1001)                      |  |
| Stainless Steel                    | 94  | (1034)                      |  |
| Expected Shear                     |   |                             | ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load |
| Room Temp (hours)                  | 20  |                             |  |
| Tack (gm/sq cm)                    | 900   |                             | ASTM D 2979  |
| Expected Exterior Life             | Indoor use only unless overlaminated with DPM® CVE or DPM® UVCG |                             |  |
| Service Temperature Range          | -40°F to 176°F (-40°C to 80°C)                                  |                             |  |
| Minimum Application<br>Temperature | 50°F (10°C)   |                             |  |
| Storage Stability                  | One year when stored at 70°F (21°C) and 50% relative humidity   |                             |  |

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 02/13/2024

