

Display Graphics

White Polypropylene Sheet (permanent) - HP Indigo Compatible

Clear and white pressure-sensitive materials for point-of-purchase displays, menu boards and general purpose signage offer a permanent or removable bond for a variety of smooth, concave and textured surfaces.

End-Use Applications:

Retail

P-O-P

Tradeshow

General-Purpose Signage

Menu Boards

For more information on FLEXcon's pressure-sensitive film solutions for Display Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX018527



Product:

**FLEXcon® DigiPRO®
DGPPWS**

Benefits:

- 3.6 mil white polypropylene film
- Topcoat is specifically designed for digital printing with HP Indigo inks and ensures excellent ink receptivity for sharp, vibrant image quality
- High-performance, aggressive permanent acrylic adhesive provides a permanent bond to a wide range of surfaces
- Adhesive has high peel and high shear characteristics resistant to cold flow and ooze
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting
- Varnishing or overlaminating is recommended to protect graphics from abrasion

Please note: this product can also be used for durable applications. Contact your Technical Service Representative for more information.

We recommend fanning the edges of the sheets prior to stacking/printing on press.



FLEXcon® DigiPRO® DGPPWS

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film	3.6 (91) +/- 10%
	Adhesive	0.9-1.0 (23-25) +/- 0.1 (3)
	Liner	6.9 (175) +/- 10%
Dimensional Stability (%)	MD	0.5
	TD	0.5
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
ABS	46	(506)
Acrylic	52	(572)
Acrylic Powder Paint	41	(451)
Epoxy Powder Paint	47	(517)
Glass	42	(462)
HDPE	23	(253)
Polyester Powder Paint	29	(319)
Polypropylene	16	(176)
Polyurethane Powder Paint	41	(451)
Stainless Steel	47	(517)
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	15	
Tack (gm/sq cm)	760	ASTM D 2979
Expected Exterior Life	Indoor use only	
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	One year when stored at 70°F (21°C) and 50% relative humidity	

Ink receptivity of this product changes over time. Please test ink adhesion before running it on machine.

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/06/2023

