

Vehicle Window Stickers

Clear Polyester - Permanent

Parking stickers are important to identify vehicles authorized to park in certain patrolled parking areas. They also are an ideal way to promote a company's logo or message. These stickers must be visible and oftentimes able to display a handwritten identification. Excellent image quality must be maintained until the sticker expires. The adhesive must bond well to auto glass and bumpers and be easy to apply. Parking stickers provide an additional means of promoting your image.

End-Use Applications:

*Parking Stickers
Oil Change Stickers
College/Alumni Decals
After-market Decals*

For more information on FLEXcon's pressure-sensitive film solutions for Vehicle Window Stickers, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX000130



Product:

**FLEXcon®
FLEXmark® PM 200 Clear
PTP V-465 90 PFW**

Benefits:

- 2.0 mil clear polyester provides excellent clarity
- Permanent acrylic pressure-sensitive adhesive bonds well to a variety of surfaces
- Adhesive resists oozing and reduces adhesive build-up for ease of diecutting
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Ideal for sheet-form converting



FLEXcon®

FLEXmark® PM 200 Clear

PTP V-465 90 PFW

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	2.0 (51) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	.7-.8 (18-20) +/- 0.1 (3)	
	Liner	6.9 (175) +/- 10%	
Dimensional Stability (%)	No Shrinkage Observed		Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
Glass	35	(385)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	5		
Tack (gm/sq cm)	440		ASTM D 2979
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/15/2024

