# **Bumper Stickers**

White - Sheet Form

Bumper stickers are like "mini-billboards", working 24/7 to get important messages across. Pressure-sensitive film is a perfect solution because it is highly durable. In addition, it offers a wide variety of options from simple, brilliant white to colors, and even eye-catching holographic patterns for interesting

light-diffraction effects.

End Use Applications: Vehicle Bumper Stickers School/Association Decals Novelty

For more information on FLEXcon's pressure-sensitive film solutions for bumper stickers, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX009648



### Product:

## Flexcon® Classics Plus® Select™ 31086SL

#### Benefits:

- 3.1 mil flexible white vinyl film provides durability and easy installation
- General-purpose emulsion acrylic adhesive used for both permanent and removable applications. Adhesive bonds well to a variety of surfaces including chrome-coated metal, chrome-coated plastic, glass, auto glass and painted plastic
- Excellent printability with UV and solvent screen inks. Please test for ink adhesion with your specific ink chemistry
- 90 lb. polycoated layflat release liner for ease of converting
- Ideal for manual dispensing



### Flexcon® Classics Plus® Select<sup>™</sup> 31086SL

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	3.1 (79) +/-10%	ASTM D 3652 (Modified for use with
	Adhesive	0.75-0.85 (19-21) +/-0.1 (3)	non-tape products)
	Liner	6.9 (175) +/-10%	
Dimensional Stability (%)	MD	0.75	Applied Shrinkage: 24 hour dwell
	TD	0.50	time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour
	Oz/In	(N/m)	dwell time)
Automotive Glass	36	(396)	
Chrome-Coated Metal	44	(484)	
Chrome-Coated Plastic	46	(506)	
Glass	30	(330)	
Painted Plastic	46	(506)	
Expected Shear			ASTM D 3654 Method A
			a. 1 hr. dwell b. 1 sq. in. surface
			c. 4 lb. load
Room Temp (hours)	2		
Tack (gm/sq cm)	350		ASTM D 2979
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years stored at 70°F (21°C) and 50% RH		

Product Performance and Suitability All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 03/04/2024

