

Durable Goods and Equipment Labeling

Clear Polyester - Overlamine

End Use Applications:

*Compliance Labels
Warning & Instructional Labels
Nameplates
Brand Identity Labels*

For Durable Goods including:

*Outdoor Power Equipment
Power Tools
Appliances
Electronics
Recreational Vehicles
Sporting Equipment
Industrial Equipment...and more*

For Transportation including:

*Automotive
Heavy Equipment*

For more information on FLEXcon's

pressure-sensitive film solutions for Durable Goods and Equipment Labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX000233



Product:

**Flexcon® Classics Plus®
10092**

Benefits:

- 1.0 mil clear polyester has excellent abrasion, humidity, chemical and solvent resistance
- Protects the underlying graphics from harsh environmental conditions
- Provides a high-gloss appearance to printed graphics
- Adhesive exhibits good clarity and cold-flow properties, resulting in good wet-out performance
- Backed with an ultra smooth clear polyester release liner for superior adhesive clarity
- UL-recognized under UL 969 - UL File No. PGGU2-MH10170 Marking and Labeling System Materials - Component
- cUL-recognized under UL 969 - File No. PGGU8.MH10170 Marking and Labeling System Materials Certified for Canada - Component
- CSA accepted under CSA File No. 99214



1 FLEXcon Industrial Park, Spencer, MA 01562-2642, Telephone (508) 885-8300 FAX (508) 885-8301 www.FLEXcon.com

Flexcon® Classics Plus® 10092

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film	1.0 (25) +/- 10%
	Adhesive	0.9-1.0 (23-25) +/- 0.1 (3)
	Liner	1.0 (25) +/- 5%
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
Acrylic	53 (583)	
Glass	28 (308)	
Metal	41 (451)	
Polyester	43 (473)	
Polyethylene	24 (264)	
Polyethylene Corona Treated	35 (385)	
Polypropylene	22 (242)	
PVC	46 (506)	
Stainless Steel	39 (429)	
Styrene	44 (484)	
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	20	ASTM D 2979
Tack (gm/sq cm)	400	
Expected Exterior Life	Two years	
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/12/2024

