Novelty Stickers

Brushed Silver
Permanent - Sheet Form

Pressure-sensitive film is the ideal choice for novelty stickers. Options range from an endless spectrum of brilliant colors, to an extensive array of specialty options like metallics, holographics, and plush, velvet-like texture.

End Use Applications
Novelty stickers
Holiday/Seasonal Decorations
Vehicle Window Stickers
Vehicle Bumper Stickers
School/Association Decals

For more information on FLEXcon's pressure-sensitive film solutions for Novelty Stickers, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX000020



Product:

Flexcon® Classics Plus® Select™ 55206SL

Benefits:

- 1.5 mil bright brushed silver polyester film offers excellent durability
- Ink-receptive surface is compatible with most UV and solvent screen inks. Please test for ink adhesion with your specific ink chemistry
- Permanent pressure-sensitive acrylic adhesive resists oozing and reduces adhesive build-up for ease of diecutting
- Adheres to a variety of surfaces including chrome-coated metal, chrome-coated plastic, glass, auto glass and painted plastic
- Sheet liner is a polycoated layflat release liner for ease of converting
- Ideal for manual dispensing



Flexcon® Classics Plus® Select™ 55206SL

| PRODUCT DATA | VALUE | | TEST METHOD |
|------------------------------------|--|-----------------------------|---|
| Physical Properties | | | |
| Thickness (Mils[microns]) | Film | 1.4 (36) +/- 10% | ASTM D 3652 (Modified for use with |
| | Adhesive | 0.9-1.0 (23-25) +/- 0.1 (3) | non-tape products) |
| | Liner | 6.9 (175) +/- 10% | |
| Dimensional Stability (%) | No Shrinkage Observed | | Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C) |
| Chemical Resistance | Water | Excellent | ASTM D 896 (Modified for number of cycles and cycle time) |
| | Gasoline | Good | |
| | Basic Cleaners | Excellent | |
| | Toluene | Good | |
| Adhesion Properties | | | |
| Ultimate Peel from | Average | | ASTM D 903 (Modified for 72 hour |
| | Oz/In | (N/m) | dwell time) |
| Auto Glass | 35 | (385) | |
| Chrome-Coated Metal | 29 | (319) | |
| Chrome-Coated Plastic | 34 | (374) | |
| Glass | 30 | (330) | |
| Painted Plastic | 38 | (418) | |
| Expected Shear | | | ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load |
| Room Temp (hours) | 10 | | |
| Tack (gm/sq cm) | 340 | | ASTM D 2979 |
| Expected Exterior Life | Two years | | |
| Service Temperature Range | -40°F to 302°F (- | 40°F to 150°C) | |
| Minimum Application Temperature | 50°F (10°C) | | |
| Storage Stability | Two years when stored at 70°F (21°C) and | | |

50% relative humidity

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 02/12/2024

