

# Graphic Mounting Film

Clear Removable/Permanent

*Flexcon® FlexMount® Select™ graphic mounting films promote easy application and excellent adhesion to a variety of surfaces for reliable and durable graphic attachments.*

*Applications Include:  
Point-of-Purchase Graphics  
Photo Mounting and Laminating  
Window Graphics  
Nameplates  
Trade Show and Event Graphics*

*For more information on FLEXcon's pressure-sensitive film solutions for Graphic Mounting Films, contact your local Sales Representative or our Performance Products Business Team at (508) 885-8440.*

*Product ID #: FLX057817*



Product:

**Flexcon®  
FlexMount® Select™  
DF492211**

Benefits:

- 1.0 mil double-faced clear polyester film ideal for applications requiring superior image quality
- Removable/repositionable adhesive provides ease during installation and clean removal of graphics
- Removable pressure-sensitive acrylic adhesive bonds well to glass, metal, and high-surface energy plastics
- Permanent overlaminating pressure-sensitive acrylic adhesive bonds well to base film surface
- Ultra-smooth polyester release liner provides excellent adhesive wetout for optimum clarity
- Backed on the other side with an ultra smooth blue polyester release liner ideal for roll-form converting
- Product can be used as a system for two-way window graphics when paired with FLEXmark® 6180 white opaque film

Create a two-sided interior mounted window graphic by printing [Flexcon® FlexMark® 6180](#) base film on both sides in right-read position. Then laminate the clear permanent side of Flexcon® FlexMount® Select™ DF492211 to the printed graphic. The blue side of FlexMount® Select™ DF492211 is removable and is adhered to the inside of the window.



# Flexcon®

## FlexMount® Select™ DF492211

PRODUCT DATA	VALUE	TEST METHOD
<b>Physical Properties</b>		
Thickness (Mils[microns])	Removable Adhesive	0.8-0.9 (20-23) +/- 0.1 (3)
	Liner	1.4 (36) +/- 10 %
	Film	1.0 (25) +/- 10 %
	Adhesive	1.0-1.1 (25-30) +/- 0.1 (3)
	Liner	1.0 (25) +/- 10 %
<b>Adhesion Properties</b>		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
Acrylic (Perm)	48	(528)
Acrylic (Remove)	29	(319)
Glass (Perm)	41	(451)
Glass (Remove)	18	(198)
Polypropylene (Perm)	10	(110)
Polypropylene (Remove)	12	(132)
Stainless Steel (Perm)	35	(385)
Stainless Steel (Remove)	21	(231)
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours) (Permanent Adhesive)	100+	
Room Temp (hours) (Removable Adhesive)	Erratic	
Tack (gm/sq cm)	300	ASTM D 2979
Tack (gm/sq cm) (Permanent Adhesive)	450	
Expected Exterior Life	Depends on substrate, both adhesives are suitable for outdoor use.	
Service Temperature Range	-20°F to 302°F (-29°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

### Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/19/2024

