

Window Graphics

Windows - Clear Vinyl - Low Tack

Window graphics draw attention and generate increased store traffic. Pressure-sensitive solutions must be easy to install, they must stay adhered over a wide-range of temperatures, allow for bold, vivid graphics that resist fading and yellowing, and be simple to remove with no adhesive residue.

*End-Use Applications:
Cooler Graphics
Window Graphics*

For more information on FLEXcon's pressure-sensitive film solutions for Window Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX019123



Product:

Flexcon®
WindowDeco™ 6541T

Benefits:

- 4.0 mil hard clear vinyl provides durability for ease of installation and removal
- Primed for excellent ink adhesion and printability via UV and conventional offset; solvent and UV screen; solvent and UV inkjet; and UV, solvent and water flexo
- Adhesive adheres well to an exterior glass surface over a wide range of temperatures
- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass surfaces while removing cleanly
- Backed with a 94 lb. premium grade moisture stable polycoated layflat release liner
- Ideal for sheetfed offset printing
- Suitable for mounting on the outside and inside of windows
- Intended for use on glass only

[Please refer to Flexcon's Window Graphics Installation Guide for more information.](#)

Caution: When using the wet application method, this product may haze. Under normal temperature and humidity conditions, the hazing usually clears within 48 hours.



Flexcon® WindowDeco™ 6541T

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	4.0 (102) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	0.8-0.9 (20-23) +/- 0.1 (3)	
	Liner	6.9 (175) +/- 10%	
Dimensional Stability (%)	MD	0.50	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	TD	0.50	
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
Glass	7	(77)	
Tack (gm/sq cm)	100		ASTM D 2979
Expected Exterior Life	One year		
Service Temperature Range	-20°F to 176°F (-29°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/05/2024

