

Primary and Secondary Labeling

Wash-Off Adhesive
Label Solution Enabling Recycling of PET Containers

*End Use Applications:
Rigid Container Labels
Semi-Squeeze Container Labels*

*For Consumable Products
including:
Beverages
Food
Health & Beauty
Household Chemical*

*For more information on
FLEXcon's
pressure-sensitive film
solutions for primary and
secondary labeling contact
your local Sales
Representative or our
Product Identification
Business Team at (508)
885-8300.*

Product ID #: FLX068848



Product:

**Flexcon®
OptiFlex® EcoFocus®
MPP 200 H Silver TC-458
V-52RE TracRite™ 120**

Benefits:

- Topcoated 1.85 mil hard silver polypropylene (BOPP) offers resistance to shrinkage, moisture, and humidity
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, narrow-format UV inkjet, UV rotary screen, UV letterpress and hot stamping
- V-52RE high-performance adhesive adheres well to PET containers
- V-52RE adhesive separates cleanly from PET flake during the recycling process allowing for the collection of rPET
- Backed with Flexcon® TracRite™ 120 polyester release liner for excellent on-press performance for tight-registration graphics
- TracRite™ 120 polyester release liner contains up to 60% Post Industrial Recycled content, provides good diecutting base and allows for high-speed dispensing
- Product has been 3rd party tested for Higher Pressure Processing (HPP) and adhesive was found to have the necessary strength and compatibility to withstand the HPP conditions

APR Critical Guidance Recognition - Flexcon's undecorated OptiFlex® EcoFocus® MPP 200 H Silver TC pressure-sensitive labels, with V-52RE adhesive meet or exceed APR's Critical Guidance Protocol for Clear PET Articles with Labels and Closures.



Flexcon®

OptiFlex® EcoFocus®

MPP 200 H Silver TC-458 V-52RE TracRite™ 120

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	1.85 (47) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)	
	Liner	1.2 (30) +/- 5%	
Dimensional Stability (%)	MD	0.5	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	TD	0.5	
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
Polyester	15	(165)	
Stainless Steel	16	(176)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	10		
Tack (gm/sq cm)	500		ASTM D 2979
Expected Exterior Life	Indoor use only		
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)		
Minimum Application Temperature	20°F (-6.6°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/04/2024

