

Durable Goods and Equipment Labeling

Clear Polyester - Overlaminates

End Use Applications:

*Compliance Labels
Warning & Instructional Labels
Nameplates
Brand Identity Labels*

For Durable Goods including:

*Outdoor Power Equipment
Power Tools
Appliances
Electronics
Recreational Vehicles
Sporting Equipment
Industrial Equipment...and more*

For Transportation including:

*Automotive
Heavy Equipment*

For more information on FLEXcon's pressure-sensitive film solutions for Durable Goods and Equipment Labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX000233



Product:

**Flexcon® Classics Plus®
10092**

Benefits:

- 1.0 mil clear polyester has excellent abrasion, humidity, chemical and solvent resistance
- Protects the underlying graphics from harsh environmental conditions
- Provides a high-gloss appearance to printed graphics
- Adhesive exhibits good clarity and cold-flow properties, resulting in good wet-out performance
- Backed with an ultra smooth clear polyester release liner for superior adhesive clarity
- UL-recognized under UL 969 - UL File No. PGGU2-MH10170 Marking and Labeling System Materials - Component
- cUL-recognized under UL 969 - File No. PGGU8.MH10170 Marking and Labeling System Materials Certified for Canada - Component
- CSA accepted under CSA File No. 99214

Flexcon® Classics Plus® 10092

PRODUCT DATA	VALUE	TEST METHOD	
Physical Properties			
Thickness (Mils[microns])	Film	1.0 (25) +/- 10%	
	Adhesive	0.9-1.0 (23-25) +/- 0.1 (3)	
	Liner	1.0 (25) +/- 5%	
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)	
Adhesion Properties			
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)	
	Oz/In (N/m)		
	Acrylic		53 (583)
	Glass		28 (308)
	Metal		41 (451)
	Polyester		43 (473)
	Polyethylene		24 (264)
	Polyethylene Corona Treated		35 (385)
	Polypropylene		22 (242)
	PVC		46 (506)
	Stainless Steel		39 (429)
	Styrene		44 (484)
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load	
Room Temp (hours)	20		
Tack (gm/sq cm)	400	ASTM D 2979	
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/12/2024

