

# Durable Goods and Equipment Labeling

Clear Gloss Polyester - Overlamine

## *End Use Applications:*

*Compliance Labels  
Warning & Instructional Labels  
Nameplates  
Brand Identity Labels*

## *For Durable Goods*

*including:*

*Outdoor Power Equipment  
Power Tools  
Appliances  
Electronics  
Recreational Vehicles  
Sporting Equipment  
Industrial Equipment...and more*

## *For Transportation including:*

*Automotive  
Aerospace  
Heavy Equipment*

*For more information on  
FLEXcon's*

*pressure-sensitive film  
solutions for Durable Goods  
and Equipment Labeling,  
contact your local Sales  
Representative or our  
Product Identification  
Business Team at (508)  
885-8300.*

*Product ID #: FLX000303*



Product: **Flexcon® DPM® Clear Gloss**

## Benefits:

- 1.0 mil clear gloss overlaminating polyester provides excellent clarity and label protection
- Overlaminating polyester resists temperature extremes, abrasion and chemical exposure for maximum label protection
- Permanent pressure-sensitive acrylic adhesive bonds well to base film substrates
- Backed with an ultra smooth clear polyester release liner
- UL recognized under UL 969 - UL File No.PGGU2.MH10170 Marking and Labeling System Materials - Component
- CSA accepted under CSA File No. 99214
- Order custom widths without purchasing a whole master through [Flexcon® FlexChoice™ for Durables](#)

# Flexcon® DPM® Clear Gloss

PRODUCT DATA	VALUE	TEST METHOD		
<b>Physical Properties</b>				
Thickness (Mils[microns])	Film	1.0 (25) +/- 10%		
	Adhesive	0.9-1.0 (23-25) +/- 0.1 (3)		
	Liner	1.0 (25) +/- 5%		
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)		
<b>Adhesion Properties</b>				
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)		
	Oz/In		(N/m)	
	Acrylic		61	(671)
	Glass		43	(473)
	Polypropylene		27	(297)
Stainless Steel	48	(528)		
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load		
Room Temp (hours)	25			
Tack (gm/sq cm)	830	ASTM D 2979		
Expected Exterior Life	Two years			
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)			
Minimum Application Temperature	50°F (10°C)			
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity			

## Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/19/2024

