

# Transfer Tape

## Single Liner

*Pressure-sensitive transfer tape adhesives are the ideal solution for mounting and bonding because they transfer easily and bond well to many challenging surfaces.*

*Markets Include:*

*Aerospace  
Appliance  
Automotive  
Consumer Electronics  
Durable Goods  
Heavy Equipment  
Industrial Equipment  
Rail*

*Applications Include:*

*Nameplate/ Brand ID  
Overlay  
Decal  
Sealing gaskets  
Gap filling  
Surface protection  
Grip, traction and anti-slip  
Noise and vibration control  
Bonding films to replace rivets  
and welds*

*For more information on FLEXcon's pressure-sensitive film solutions for Transfer Tapes, contact your local Sales Representative or our Performance Products Business Team at (508) 885-8440.*

*Product ID #: FLX000488*



Product:

**FLEXcon®  
FLEXmount® TT 200 L-606  
60 LA PFW**

Benefits:

- Permanent acrylic adhesive offers medium tack, high shear and excellent adhesion to a variety of metal and plastic surfaces, including polypropylene, polyethylene, PORON® and Kushon® cellular rubber products
- Backed with a 60 lb. bleached white kraft liner, polycoated and release coated on two sides
- Adhesive exhibits exceptional performance on textured and uneven surfaces
- Release liner has excellent moisture stability and is a good base for rotary, flatbed and steel rule diecutting
- Product is ideal for smooth surface applications
- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

# FLEXcon® FLEXmount® TT 200 L-606 60 LA PFW

| PRODUCT DATA                    | VALUE   | TEST METHOD   |
|---------------------------------|---|---|
| <b>Physical Properties</b>      |   |   |
| Thickness (Mils[microns])       | Adhesive 1.9-2.1 (48-53) +/- 0.1 (3)<br>60 LA PFW 4.3 (109) +/- 10% | ASTM D 3652 (Modified for use with non-tape products)                           |
| Expected Shear                  |   | ASTM D 3654 Method A<br>a. 1 hr. dwell<br>b. 1 sq. in. surface<br>c. 4 lb. load |
| Room Temp (hours)               | 30  |   |
| Tack (gm/sq cm)                 | 1650  | ASTM D 2979   |
| Expected Exterior Life          | Dependant on life of substrate - suitable for outdoor use           |   |
| Service Temperature Range       | -40°F to 302°F (-40°C to 150°C)                                     |   |
| Minimum Application Temperature | 50°F (10°C)   |   |
| Storage Stability               | Two years when stored at 70°F (21°C) and 50% relative humidity      |   |

For the Complete Product Data View: [FLEXmount® L-606/V-606 Adhesive Series Data Sheet](#)

#### Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/06/2024

