Safety / Visibility Applications

Engineering Grade Retroreflective

End Use Applications including:
Component Tracking Labels Warning & Instructional Labels Outdoor Safety Signage Promotional Labels Long-range Barcode Labels Warehouse WIP Labels, Shelf Marking
Supply Chain Management

Custom colors available.

For more information on FLEXcon's pressure-sensitive film solutions for Safety / Visibility Applications, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX009586



Product:

FLEXcon® REFLECTAmark® WEGS

Benefits:

- 2 mil acrylic film with 2 mil reflective glass bead coating
- Compatible with a wide range of conventional print methods (we recommend evaluating the intended ink system for compatibility with the product under the application conditions)
- Excellent chemical and scratch resistance
- High-performance permanent acrylic adhesive bonds well to ABS, aluminum and stainless steel surfaces
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting
- 7 year outdoor durability



FLEXcon® REFLECTAmark® WEGS

PRODUCT DATA VALUE TEST METHOD

Physical Properties

Thickness (Mils[microns]) Film & Coating 4.0 (102) +/- 15% ASTM D 3652 (Modified for use with

Adhesive 1.2-1.3 (30-33) +/- 0.1 (3) non-tape products)

Liner 6.9 (175) +/- 10%

Dimensional Stability (%) MD 0.50 Applied Shrinkage: 24 hour dwell

TD 0.50 time on aluminum panel then 24 hours at 160°F (71°C)

Adhesion Properties

Ultimate Peel from Average ASTM D 903 (Modified for 72 hour

Oz/In (N/m) dwell time)

Acrylic Film rips during

the adhesion test

Glass Film rips during

the adhesion test

Stainless Steel Film rips during

the adhesion test

Expected Shear ASTM D 3654 Method A

a. 1 hr. dwellb. 1 sq. in. surfacec. 4 lb. load

Room Temp (hours) 10

Tack (gm/sq cm) 850 ASTM D 2979

Expected Exterior Life Seven years

Service Temperature Range -40°F to 176°F (-40°C to 80°C)

Minimum Application 50°F (10°C)

Temperature

Storage Stability Two years when stored at 70°F (10°C) and

50% relative humidity

FOR REFLECTIVITY DATA, CLICK HERE.

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/06/2024

