

Window Graphics

White Vinyl - Low Tack HP Indigo Printable

Window graphics draw attention and generate increased store traffic. Pressure-sensitive solutions must be easy to install, they must stay adhered over a wide-range of temperatures, allow for bold, vivid graphics that resist fading and yellowing, and be simple to remove with no adhesive residue.

*End-Use Applications:
Window Graphics
Backlit Window Graphics*

For more information on FLEXcon's pressure-sensitive film solutions for Window Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX026312



Product:

**Flexcon®
WindowDeco™ 6230DG**

Benefits:

- 3.5 mil flexible white vinyl provides durability for ease of installation and removal
- Topcoat is specifically designed for digital printing with HP Indigo inks and ensures excellent ink receptivity for sharp vibrant image quality
- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass surfaces while removing cleanly
- Once applied, adhesive adheres well to an exterior glass surface over a wide range of temperatures
- Backed with a 94 lb. premium grade moisture stable polycoated layflat release liner
- Suitable for mounting on the outside and inside of windows
- Varnishing or overlaminating is recommended to protect the graphics from abrasion

[Please refer to Flexcon's Window Graphics Installation Guide for more information.](#)

Flexcon® WindowDeco™ 6230DG

| PRODUCT DATA | VALUE | TEST METHOD |
|---------------------------------|---|--|
| Physical Properties | | |
| Thickness (Mils[microns]) | Film | 3.5 (89) +/- 10% |
| | Adhesive | 0.8-0.9 (20-23) +/- 0.1 (3) |
| | Liner | 6.9 (175) +/- 10% |
| Dimensional Stability (%) | MD | 0.50 |
| | TD | 0.50 |
| Adhesion Properties | | |
| Ultimate Peel from | Average | ASTM D 903 (Modified for 72 hour dwell time) |
| | Oz/ln | |
| Non-tinted Glass | 13 | (143) |
| Tack (gm/sq cm) | 70 | ASTM D 2979 |
| Expected Exterior Life | One year | |
| Service Temperature Range | -20°F to 176°F (-29°C to 80°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | One year when stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/05/2024

