

Window Graphics

Clear Non-Vinyl- Low Tack

Window graphics draw attention and generate increased store traffic. Pressure-sensitive solutions must be easy to install, they must stay adhered over a wide-range of temperatures, allow for bold, vivid graphics that resist fading and yellowing, and be simple to remove with no adhesive residue.

*End-Use Applications:
Window Graphics
Backlit Window Graphics*

For more information on FLEXcon's pressure-sensitive film solutions for Window Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX028903



Product:

Flexcon®
WindowDeco™ 6272

Benefits:

- 3.6 mil flexible clear polyolefin (non-vinyl "greener") film with a smooth surface for graphic reproduction
- Phthalate free and produced with less solvent as compared to solvent adhesive systems
- Complies with CONEG and CPSIA
- Printable via UV and solvent screen, and UV inkjet
- When printed UV, VOCs emissions are reduced yielding less impact on the environment
- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass surfaces while removing cleanly
- Adhesive adheres well to an exterior glass surface over a wide range of temperatures
- Suitable for mounting on the outside and inside of windows
- Backed with a 94 lb. premium grade moisture stable polycoated layflat release liner
- Overlaminating will extend the life of the graphic - contact your Flexcon Technical Service representative for more information

Definitions: CONEG = Northeastern Governors; CPSIA = Consumer Products Safety Improvement Act; and VOCs = Volatile Organic Compounds).

[Please refer to Flexcon's Window Graphics Installation Guide for more information.](#)

For Inkjet Printing:

- Typical max. ink limit = 250%;
- When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

Flexcon® WindowDeco™ 6272

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	3.6 (91) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	0.8-0.9 (20-23) +/- 0.1 (3)	
	Liner	6.9 (175) +/- 10%	
Dimensional Stability (%)	MD	0.25	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	TD	0.25	
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
Non-tinted Glass	6	(66)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	15		
Tack (gm/sq cm)	370		ASTM D 2979
Expected Exterior Life	Up to one year		
Service Temperature Range	-20°F to 176°F (-29°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/05/2024

