

Bumper Stickers

Yellow - Sheet Form

Bumper stickers are like "mini-billboards", working 24/7 to get important messages across. Pressure-sensitive film is a perfect solution because it is highly durable. In addition, it offers a wide variety of options from simple, brilliant white to colors, and even eye-catching holographic patterns for interesting light-diffraction effects.

*End Use Applications:
Vehicle Bumper Stickers
School/Association Decals
Novelty
Vehicle Window Stickers
Flexible Magnet*

For more information on FLEXcon's pressure-sensitive film solutions for Bumper Stickers, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX000028



Product:

**Flexcon®
FlexMark® V 400 F Yellow
TC-848 V-465 Spec 50K-8**

Benefits:

- 3.5 mil flexible vinyl film for easy application
- Black, red and yellow film is available for high visual appeal
- Topcoat optimizes printability with most standard flexographic inks. (Please test for ink adhesion with your specific ink chemistry.)
- Permanent pressure-sensitive acrylic adhesive bonds well to a variety of surfaces including paper, wood, glass and metal
- Backed with a 50 lb. bleached kraft release liner that provides an excellent diecutting base
- Ideal for roll-form converting

Flexcon®
FlexMark® V 400 F Yellow
TC-848 V-465 Spec 50K-8

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film	3.5 (89) +/- 10%
	Adhesive	0.75-0.85 (19-22) +/- 0.1 (3)
	Liner	3.1 (79) +/- 10%
Dimensional Stability (%)	MD	0.75
	TD	0.75
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/ln	(N/m)
	Glass	45 (495)
	Painted Metal	43 (473)
	Painted Wallboard	15 (165)
	Painted Wood	11 (121)
	Paper	36 (396)
	Varnished Wood	23 (253)
	Vinyl	41 (451)
	Expected Shear	
Room Temp (hours)	8	
Tack (gm/sq cm)	230	ASTM D 2979
Expected Exterior Life	Two years (vertical exposure, mid-continental US)	
Service Temperature Range	-20°F to 176°F (-29°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/15/2024

