

# Primary and Secondary Labeling

Clear Polypropylene

*Get the No-Label-Look  
Required for Your  
Application*

*End Use Applications:  
Rigid Container Labels  
Semi-Squeeze Container Labels*

*For Consumable Products  
including:  
Beverage  
Food  
Health & Beauty  
Household Chemical*

*For more information on  
FLEXcon's  
pressure-sensitive film  
solutions for Primary and  
Secondary Container  
Labeling, contact your local  
Sales Representative or our  
Product Identification  
Business Team at (508)  
885-8300.*

*Product ID #: FLX056456*



Product:

**Flexcon®**  
**OptiFlex® CPP20413**  
PP 200 H Clear TC-458 V-01 TracRite™ 120

Benefits:

- Topcoated 2.0 mil hard clear polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film clarity is ideal for achieving the no-label-look
- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, UV inkjet (Xeikon Jetrion 4000 series and Domino), UV screen, UV letterpress, and hot stamping
- V-01 high-performance, permanent acrylic adhesive adheres to a wide range of container types including low-surface energy HDPE
- Adhesive complies with FDA 175.105 for indirect food contact
- Backed with Flexcon® TracRite™ 120 polyester release liner for excellent on-press performance for tight registration graphics
- Release liner provides a good diecutting base and allows for high-speed dispensing
- Product has been 3rd party tested for Higher Pressure Processing (HPP) and adhesive was found to have the necessary strength and compatibility to withstand the HPP conditions
- Order custom widths without purchasing a whole master through [Flexcon®](#) [FLEXchoice™ for Prime Label](#)

# Flexcon® OptiFlex® CPP20413

PP 200 H Clear TC-458 V-01 TracRite™ 120

PRODUCT DATA	VALUE	TEST METHOD
<b>Physical Properties</b>		
Thickness (Mils[microns])	Film	2.0 (51) +/- 10 %
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)
	Liner	1.2 (30) +/- 5 %
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
<b>Adhesion Properties</b>		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
Acrylic	54 (594)	
Glass	40 (440)	
HDPE	18 (198)	
Polyester	39 (429)	
Polypropylene	23 (253)	
Stainless Steel	54 (594)	
Styrene	41 (451)	
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	10	
Tack (gm/sq cm)	790	ASTM D 2979
Expected Exterior Life	Indoor use only	
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/25/2024

