Promotional Advertising

Clear Velvet Overlaminate

Point-of-purchase displays attract consumer attention and lead to immediate sales. Eye-catching pressure-sensitive films are available in every color imaginable, from simple colors to complex microembossed films and glow-in-the-dark films, as well as flocked vinyl with a suede-like feel. Pressure-sensitive adhesives offer a permanent or removable bond for a variety of smooth, concave or textured surfaces.

End Use Applications: Retail Displays P-O-P Displays Tradeshow Displays

For more information on FLEXcon's pressure-sensitive film solutions for Promotional Advertising, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX000365



Product:

Flexcon® FlexMark® OV 400 H Clear Velvet V-29 71B PMO-8

Benefits:

- 4.0 mil clear velvet vinyl is durable and resists scratches and fingerprints
- Film protects the underlying graphics from harsh environmental conditions
- Permanent overlaminating pressure-sensitive acrylic adhesive bonds well to base film surface
- Backed with a 71 lb. smooth bleached white polycoated kraft release liner ideal for roll-form converting



Flexcon® FlexMark® OV 400 H Clear Velvet V-29 71B PMO-8

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film Adhesive Liner	4.3 (109) +/- 10% 1.4-1.5 (36-38) +/- 0.1 (3) 4.3 (109) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
Dimensional Stability (%)	MD TD	0.5 0.5	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average Oz/In	(N/m)	ASTM D 903 (Modified for 72 hour dwell time)
Acrylic	123	(1353)	
Glass	98	(1078)	
Polypropylene	17	(187)	
Stainless Steel	101	(1111)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	100+		
Tack (gm/sq cm)	370		ASTM D 2979
Expected Exterior Life	One year		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 02/14/2024

