

# Vehicle Window Stickers

Clear Polyester - Permanent

*Parking stickers are important to identify vehicles authorized to park in certain patrolled parking areas. They also are an ideal way to promote a company's logo or message. These stickers must be visible and oftentimes able to display a handwritten identification. Excellent image quality must be maintained until the sticker expires. The adhesive must bond well to auto glass and bumpers and be easy to apply. Parking stickers provide an additional means of promoting your image.*

*End-Use Applications:  
Parking Stickers  
Oil Change Stickers  
College/Alumni Decals  
After-market Decals*

*For more information on FLEXcon's pressure-sensitive film solutions for Vehicle Window Stickers, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.*

*Product ID #: FLX000130*



Product:

**FLEXcon®  
FLEXmark® PM 200 Clear  
PTP V-465 90 PFW**

Benefits:

- 2.0 mil clear polyester provides excellent clarity
- Permanent acrylic pressure-sensitive adhesive bonds well to a variety of surfaces
- Adhesive resists oozing and reduces adhesive build-up for ease of diecutting
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Ideal for sheet-form converting

# FLEXcon®

## FLEXmark® PM 200 Clear

### PTP V-465 90 PFW

| PRODUCT DATA                    | VALUE  |                           | TEST METHOD   |
|---------------------------------|--|---------------------------|---|
| Physical Properties             |  |                           |   |
| Thickness (Mils[microns])       | Film   | 2.0 (51) +/- 10%          | ASTM D 3652 (Modified for use with non-tape products)                                 |
|                                 | Adhesive   | .7-.8 (18-20) +/- 0.1 (3) |   |
|                                 | Liner  | 6.9 (175) +/- 10%         |   |
| Dimensional Stability (%)       | No Shrinkage Observed  |                           | Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C) |
| Adhesion Properties             |  |                           |   |
| Ultimate Peel from              | Average  |                           | ASTM D 903 (Modified for 72 hour dwell time)  |
|                                 | Oz/In  | (N/m)                     |   |
| Glass                           | 35   | (385)                     |   |
| Expected Shear                  |  |                           | ASTM D 3654 Method A<br>a. 1 hr. dwell<br>b. 1 sq. in. surface<br>c. 4 lb. load       |
| Room Temp (hours)               | 5  |                           |   |
| Tack (gm/sq cm)                 | 440  |                           | ASTM D 2979   |
| Expected Exterior Life          | Two years  |                           |   |
| Service Temperature Range       | -40°F to 302°F (-40°C to 150°C)                                |                           |   |
| Minimum Application Temperature | 50°F (10°C)  |                           |   |
| Storage Stability               | Two years when stored at 70°F (21°C) and 50% relative humidity |                           |   |

#### Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/15/2024

