

Vehicle Window Stickers

Clear Polyester - Permanent

Parking stickers are important to identify vehicles authorized to park in certain patrolled parking areas. They also are an ideal way to promote a company's logo or message. These stickers must be visible and oftentimes able to display a handwritten identification. Excellent image quality must be maintained until the sticker expires. The adhesive must bond well to auto glass and bumpers and be easy to apply. Parking stickers provide an additional means of promoting your image.

End-Use Applications:

*Parking Stickers
Oil Change Stickers
College/Alumni Decals
After-market Decals*

For more information on FLEXcon's pressure-sensitive film solutions for Vehicle Window Stickers, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX000130



Product:

**FLEXcon®
FLEXmark® PM 200 Clear
PTP V-465 90 PFW**

Benefits:

- 2.0 mil clear polyester provides excellent clarity
- Permanent acrylic pressure-sensitive adhesive bonds well to a variety of surfaces
- Adhesive resists oozing and reduces adhesive build-up for ease of diecutting
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Ideal for sheet-form converting

FLEXcon® FLEXmark® PM 200 Clear PTP V-465 90 PFW

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film	2.0 (51) +/- 10%
	Adhesive	.7-.8 (18-20) +/- 0.1 (3)
	Liner	6.9 (175) +/- 10%
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
Glass	35 (385)	
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	5	
Tack (gm/sq cm)	440	ASTM D 2979
Expected Exterior Life	Two years	
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/15/2024

