## **Display Graphics**

White Vinyl

Clear and white pressure-sensitive materials for point-of-purchase displays and general purpose signage offer a permanent or removable bond for a variety of smooth, concave and textured surfaces.

End-Use Applications: P-O-P Displays General-Purpose Signage

For more information on FLEXcon's pressure-sensitive film solutions for Display Graphics, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX000115



Product: Flexcon® Classics Plus® 41006

## Benefits:

- 3.5 mil semi-flexible white vinyl film resists on-liner and applied shrinkage
- Excellent printability via UV and solvent screen, and UV litho
- Permanent pressure-sensitive acrylic adhesive bonds well to a variety of surfaces, including low-surface energy plastics
- Backed with a layflat 90 lb. moisture stable polycoated release liner ideal for sheet-form converting



## Flexcon® Classics Plus® 41006

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film Adhesive Liner	3.5 (89) +/- 10% 1.0-1.1 (25-28) +/- 0.1 (3) 6.9 (175) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
Dimensional Stability (%)	MD TD	<1.0 <1.0	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Chemical Resistance	Water Gasoline Basic Cleaners Toluene	Good Fair Good Poor	ASTM D 896 (Modified for number of cycles and cycle time)
Adhesion Properties	<b>A</b>		ACTNA D 000 (NA - 1/5 - 1 fee 70 h
ABS Acrylic Coroplast - Corrugated Board Glass Painted Metal Painted Wood Paper Polycarbonate Polyethylene Polypropylene Sintra - Foam Board Stained and Varnished Wood	Average Oz/In 71 73 63 70 52 22 7+ 76 27 32 59 24	(N/m) (781) (803) (693) (770) (572) (242) (77+) (836) (297) (352) (649) (264)	ASTM D 903 (Modified for 72 hour dwell time)
Styrene Expected Shear	70	(770)	ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours) Tack (gm/sq cm) Expected Exterior Life Service Temperature Range Minimum Application	10 370 Two Years -40°F to 176°F ( 50°F (10°C)	40°C to 80°C)	ASTM D 2979
Temperature	T		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you

after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 02/12/2024



Storage Stability