

# Durable Goods and Equipment Labeling

Flexible White Vinyl - Sheet Form

## *End Use Applications:*

*Compliance Labels  
Warning & Instructional Labels  
Nameplates  
Brand Identity Labels*

## *For Durable Goods including:*

*Outdoor Power Equipment  
Power Tools  
Appliances  
Electronics  
Recreational Vehicles  
Sporting Equipment  
Industrial Equipment...and more*

## *For Transportation including:*

*Automotive  
Aerospace  
Heavy Equipment*

*For more information on FLEXcon's pressure-sensitive film solutions for Durable Goods and Equipment Labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.*

*Product ID #: FLX000308*



## Product:

**Flexcon® DPM® FWS**

## Benefits:

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Compatible with most conventional and UV ink systems (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions)
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting
- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component
- CSA accepted under CSA File No. 99214
- Order custom widths without purchasing a whole master through [Flexcon® FlexChoice™ for Durables](#)

# Flexcon® DPM® FWS

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	3.5 (89) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	1.0-1.1 (25-28) +/- 0.1 (3)	
	Liner	6.9 (175) +/- 10%	
Dimensional Stability (%)	MD	0.75	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	TD	0.75	
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
Acrylic	69	(759)	
Glass	64	(704)	
Polypropylene	24	(264)	
Stainless Steel	101	(1111)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	15		
Tack (gm/sq cm)	750		ASTM D 2979
Expected Exterior Life	Five years based on 2000 hrs Xenon Arc testing		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

## Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 04/11/2024

