

Promotional Advertising

Topcoated Clear Vinyl - Permanent

Self-adhesive film is an essential tool for indoor and outdoor promotional advertising, providing the durability, flexibility, and aesthetic quality that open up all kinds of possibilities for grabbing the consumer's attention for the duration of the advertising campaign.

End-Use Applications:

*Cooler Graphics
Counter Graphics
Display Graphics
General-Purpose Signage
Interior Signage
Outdoor Signage
Wall Graphics
Window Graphics*

For more information on FLEXcon's pressure-sensitive film solutions for Promotional Advertising, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX059981



Product:

**Flexcon®
FlexMark® CPT**

Benefits:

- 4.0 mil hard clear vinyl provides durability for ease of installation and removal
- High-performance permanent adhesive bonds well to ABS, acrylic, Formica®, aluminum, stainless steel, HDPE, painted metal, styrene, painted non-vinyl wallboard, glass and more
- Primed for excellent ink adhesion and printability via UV and conventional offset, solvent and UV screen, solvent and water flexo, and solvent and UV inkjet
- 90 lb. polycoated layflat release liner for ease of converting

For Inkjet Printing:

- Typical max. ink limit = 250%;
- When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

Formica® is a registered trademark of the Diller Corp.



1 Flexcon Industrial Park, Spencer, MA 01562-2642, Telephone (508) 885-8370 FAX (508) 885-8399 www.flexcon.com

Flexcon® FlexMark® CPT

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	4.0 (102) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	0.9-1.0 +/- 0.1 (3)	
	Liner	6.9 (175) +/- 10%	
Dimensional Stability (%)	MD	0.75	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	TD	0.50	
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
ABS	110	(1210)	
Acrylic Powder Paint	101	(1111)	
Aluminum	73	(803)	
Formica	48	(528)	
Glass	96	(1056)	
HDPE	41	(451)	
Painted Metal	90	(990)	
Painted Wood	35	(385)	
Polycarbonate	91	(1001)	
Polypropylene	43	(473)	
Sintra	65	(715)	
Smooth Painted (non-vinyl) Wallboard	25	(275)	
Stainless Steel	87	(957)	
Styrene	73	(803)	
Varnished Wood	45	(495)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	15		
Tack (gm/sq cm)	1000		ASTM D 2979
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years stored at 70°F (21°C) and 50% RH		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/04/2024

