

# Resealable Closure

White Polypropylene

*Designed For Resealable  
Packaging Including:*

*Wet and Dry Wipes for  
Health and Beauty  
Household Chemical*

*For more information on  
FLEXcon's  
pressure-sensitive film  
solutions for resealable  
closure contact your local  
Sales Representative or our  
Product Identification  
Business Team at (508)  
885-8300.*

*Product ID #: FLX064717*



Product:

**Flexcon®**  
**OptiFlex® Reseal™ 21133**  
2.3 Mil White BOPP TC, Resealable Adhesive,  
TracRite™ 120

## Benefits:

- 2.3 mil white polypropylene (BOPP) offers excellent tear resistance and durability for open and closure of flexible packaging substrates
- Superior film conformability provides maximum label and graphic coverage
- Film opacity is ideal for achieving high visual impact
- Excellent surface smoothness allows for optimum ink laydown
- Polypropylene film offers good diecutting properties and excellent resistance to moisture, humidity and product contents
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping
- Resealable pressure-sensitive acrylic adhesive bonds well to low- and high- surface energy laminated flexible packaging substrates with clean, quiet and consistent reclosure
- Adhesive complies with 21 CFR 175.105 for indirect food contact
- Adhesive offers excellent clarity and wet out characteristics
- Release liner provides excellent surface smoothness for good adhesive wet out and serves as an excellent diecutting base for flexible substrates
- Order custom widths without purchasing a whole master through [Flexcon®](#) [FLEXchoice™ for Prime Label](#)

# Flexcon®

## OptiFlex® Reseal™ 21133

2.3 Mil White BOPP TC, Resealable Adhesive, TracRite™ 120

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	2.3 (56) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	0.7 - 0.8 (18-20) +/- 0.1 (3)	
	Liner	1.2 (30) +/-10%	
Dimensional Stability (%)	No Shrinkage Observed		Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
Acrylic	22	(242)	
Glass	15	(165)	
Polypropylene	13	143	
Stainless Steel	16	(176)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	100+		ASTM D 2979
Tack (gm/sq cm)	440		
Expected Exterior Life	Indoor use only		
Service Temperature Range	-20°F to 212°F (-29°C to 100°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years stored at 70°F (21°C) and 50% RH		

### Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/19/2024

