

Large Diameter Labeling for OTC Drugs

White Polypropylene, Poly Liner

*End Use Applications:
Track & Trace, and Branding &
Graphics for Pill Containers*

*Suitable for autoclave, ethylene
oxide, gamma and electron
beam sterilization methods.*

*For more information on
FLEXcon's
pressure-sensitive film
solutions for OTC
Pharmaceutical Labeling,
contact your local Sales
Representative or our
Product Identification
Business Team at (508)
885-8300.*

Product ID #: FLX068903



Product:

Flexcon®
PharmCal® OTC 068903
(PharmCal® PP 230 H White
TC-458 V-449 TracRite™ 120)

Benefits:

- 2.3 mil hard white polypropylene offers excellent resistance to shrinkage, high temperatures, moisture, humidity and product contents
- Film opacity is ideal for achieving high-image graphics
- Conformable film contours around cylindrical packaging
- Print-receptive surface is printable via flexographic, UV offset, gravure, UV screen, UV letterpress, thermal transfer, narrow-format UV inkjet, and hot stamping
- Permanent high-tack, high-peel adhesive with excellent performance on plastic containers
- Flexcon® TracRite™ 120 polyester release liner provides excellent on-press performance for tight-registration graphics
- Liner provides an excellent die cutting base, and allows for high-speed dispensing and matrix stripping
- Meets Compliance Regulations: 21 CFR 175.105, RoHS/WEE, and REACH
- 3-month change notification

*FDA CFR 175.105: Adhesives may be safely used as components of articles intended for use in packaging, transporting, or holding food in accordance with the following prescribed conditions.

“Fit-for-use” testing is recommended under actual application conditions.

Flexcon®
PharmCal® OTC 068903
(PharmCal® PP 230 H White
TC-458 V-449 TracRite™ 120)

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film	2.3 (58) +/- 10%
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)
	Liner	1.2 (30) +/- 5%
Dimensional Stability (%)	No Shrinkage Observed	ASTM D 3652 (Modified for use with non-tape products) Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
Glass	40 (440)	
Polypropylene	23 (253)	
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	10	
Tack (gm/sq cm)	790	ASTM D 2979
Expected Exterior Life	Indoor use only	
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/16/2024

