## **High Temp**

Foil with Flame-Retardant Adhesive

Applications include: Lamination & Fabrication

For more information on FLEXcon's pressure-sensitive film solutions for lamination and fabrication, contact your local Sales Representative or our Performance Products Business Team at (508) 885-8440.

Product ID #: FLX068878



Product:

Flexcon® FlexMark® L-59FR 068878 (2.0 Mil Foil, 4.0 Mil Adhesive)

## Benefits:

- 2.0 mil aluminum foil for supreme heat resistance
- 4.0 mil white flame-retardant non-halogenated adhesive
- Adhesive adheres well to acrylic, polypropylene, stainless steel, polyethylene, and glass
- 50 lb. bleached kraft release liner offers good diecutability
- Liner ideal for roll converting and manual dispensing
- FlexMark® L-59FR products at a 2.0 mil to 4.0 mil adhesive thickness are rated UL 94 V-0 when coated on 2.0 mil polyimide and 2.0 mil aluminum foil (UL E518655)



## Flexcon® FlexMark® L-59FR 068878 (2.0 Mil Foil, 4.0 Mil Adhesive)

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	2.0 (51) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	3.9-4.1 (99-104) +/- 0.1 (3)	
	Liner	3.1 (79) +/- 10%	
Dimensional Stability (%)	No Shrinkage Observed		Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour
	Oz/In	(N/m)	dwell time)
Acrylic	57	(627)	
Glass	61	(671)	
Polyethylene	18	(198)	
Polypropylene	11	(121)	
Stainless Steel	50	(550)	
Expected Shear			ASTM D 3654 Method A
			a. 1 hr. dwell b. 1 sq. in. surface
			c. 4 lb. load
Room Temp (hours)	100		
Tack (gm/sq cm)	1040		ASTM D 2979
Flammability	See other side for information		
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50%		

relative humidity

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 02/14/2024

