.002" (2.0 Mil) Roll Form Laminating Adhesive with Flame-Retardant Adhesive

Aerospace applications include:

- floor coverings
- textiles (draperies & upholstery)
- seat cushions
- padding
- trays
- electrical conduits
- air ducting
- cargo covers

For more information on FLEXcon's pressure-sensitive film solutions for aerospace, contact your local Sales Representative or our Performance Products Business Team at (508) 885-8440.

Product ID #: FLX068228



Product:

Flexcon® FlexMount® L-59FR 068228 (2.0 Mil Transfer Tape, Double 50# Liner)

Benefits:

- 2.0 mil white flame-retardant adhesive
- Adhesive adheres well to acrylic, polypropylene, stainless steel, polyethylene, and glass
- Product is ideal for smooth surfaces applications
- Backed with two 50 lb. semi-bleached white kraft release liners ideal for roll-to-roll converting
- FlexMount® L-59FR products at a 2.0 mil to 4.0 mil adhesive thickness are rated UL 94 V-0 when bonded to 2.0 mil polyimide and 2.0 mil aluminum foil (UL E518655)
- FlexMount® L-59FR products at a 2.0 mil adhesive thickness pass the following test standards:
 Vertical 60 sec burn: FAR 25.853

 (a) Appendix F, Part I, (a), 1, (i);
 Vertical 12 sec burn: FAR 25.853
 (a) Appendix F, Part I, (a), 1, (ii);
 Heat Release: FAR 25.853 (d)
 Appendix F, Part IV; Smoke
 Density: FAR 25.853 (d) Appendix
 F, Part V; Toxicity Test: BSS 7239



Flexcon® FlexMount® L-59FR 068228 (2.0 Mil Transfer Tape, Double 50# Liner)

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	50K-6 Adhesive Spec 50K-9	3.1 (79) +/- 10/% 1.9-2.1 (48-53) +/- 0.1 (3) 3.1 (79) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	100		
Tack (gm/sq cm)	980		ASTM D 2979
Flammability	See other side for information		
Expected Exterior Life	Depends on substrate, adhesive is suitable for outdoor use		
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

For guidance only - the data are based on three or less production runs.

DISCLAIMER: FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE. This product is a device component intended solely for further processing, manufacturing, or incorporation into a finished device. Customer is solely responsible for determining whether this component product is fit for Customer's intended use, including, without limitation, incorporation into Customer's finished device(s), and for performing any additional testing that may be necessary to support Customer's intended use. Customer is solely responsible for ensuring that its use of the component product is in compliance with the applicable laws and for obtaining any necessary clearances or approvals from its use of the component product and any finished device that incorporates the component product. Full flame-retardant test results are available upon request.

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 03/12/2025

