

Aerospace

.002" (2.0 Mil) Roll Form Laminating Adhesive
with Flame-Retardant Adhesive

Aerospace applications include:

- floor coverings
- textiles (draperies & upholstery)
- seat cushions
- padding
- trays
- electrical conduits
- air ducting
- cargo covers

For more information on FLEXcon's pressure-sensitive film solutions for aerospace, contact your local Sales Representative or our Performance Products Business Team at (508) 885-8440.

Product ID #: FLX068345



Product:

**FLEXcon®
FLEXmount® L-59FR 068345
(2.0 Mil Transfer Tape,
84# Liner)**

Benefits:

- 2.0 mil white flame-retardant adhesive
- Adhesive adheres well to acrylic, polypropylene, stainless steel, polyethylene, and glass
- Backed with an 84 lb. natural kraft polycoated layflat differential release liner ideal for roll-to-sheet converting
- Heavy release liner has excellent moisture stability and is a good base for flatbed and steel rule diecutting
- Product is ideal for smooth surface applications
- FLEXmount® L-59FR products at a 2.0 mil to 4.0 mil adhesive thickness are rated UL 94 V-0 when bonded to 2.0 mil polyimide and 2.0 mil aluminum foil (UL E518655)
- FLEXmount® L-59FR products at a 2.0 mil adhesive thickness pass the following test standards:
Vertical 60 sec burn: FAR 25.853 (a) Appendix F, Part I, (a), 1, (i);
Vertical 12 sec burn: FAR 25.853 (a) Appendix F, Part I, (a), 1, (ii);
Heat Release: FAR 25.853 (d) Appendix F, Part IV; Smoke Density: FAR 25.853 (d) Appendix F, Part V; Toxicity Test: BSS 7239

FLEXcon®
FLEXmount® L-59FR 068345
(2.0 Mil Transfer Tape,
84# Liner)

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Adhesive	1.9-2.1 (48-53) +/- 0.1 (3)
	Liner	6.4 (163) +/- 10%
Expected Shear		ASTM D 3652 (Modified for use with non-tape products)
Room Temp (hours)	100	ASTM D 3654 Method A
Tack (gm/sq cm)	980	a. 1 hr. dwell
Flammability	See other side for information	b. 1 sq. in. surface
Expected Exterior Life	Depends on substrate, adhesive is suitable for outdoor use	c. 4 lb. load
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	ASTM D 2979
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

For guidance only - data are based on three or less production runs.

DISCLAIMER: FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE. This product is a device component intended solely for further processing, manufacturing, or incorporation into a finished device. Customer is solely responsible for determining whether this component product is fit for Customer's intended use, including, without limitation, incorporation into Customer's finished device(s), and for performing any additional testing that may be necessary to support Customer's intended use. Customer is solely responsible for ensuring that its use of the component product is in compliance with the applicable laws and for obtaining any necessary clearances or approvals from its use of the component product and any finished device that incorporates the component product. Full flame-retardant test results are available upon request.

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 03/12/2025

