

# Consumer Durables

Gloss Topcoated Silver Polyester  
Air Egress Sheet Form Liner

## *End Use Applications:*

*Compliance Labels  
Warning & Instructional Labels  
Nameplates  
Brand Identity Labels*

## *Markets including:*

*Appliance  
Heavy/Outdoor Equipment  
Industrial/Manufacturing  
Power Equipment  
Recreational Vehicles*

*For more information on  
FLEXcon's  
pressure-sensitive film  
solutions for Consumer  
Durables, contact your local  
Sales Representative or our  
Product Identification  
Business Team at (508)  
885-8300.*

*Product ID #: FLX069799*



Product: **Flexcon® DPM Aply® 2SPSAE  
(MM 200 Silver TC-716 L-344  
90 PFW Air Egress - UL Rec)**

## Benefits:

- Gloss topcoated 2.0 mil silver polyester provides consistent surface smoothness, excellent dimensional stability, and endurance to varying temperatures
- Silver polyester provides a high-end appearance
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); and narrow-format UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- 90 lb. embossed liner creates air egress channels in the adhesive to eliminate bubbles and wrinkles during application process and post application process
- Liner is ideal for roll-to-sheet and sheet-form converting on most narrow-format presses
- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing.

For laser diecutability, please check with your equipment manufacturer.

Please note: DPM Aply® with air egress liner is available for sale in North America only.



**Flexcon® DPM Aply® 2SPSAE  
(MM 200 Silver TC-716 L-344  
90 PFW Air Egress - UL Rec)**

PRODUCT DATA	VALUE	TEST METHOD	
<b>Physical Properties</b>			
Thickness (Mils[microns])	Film	2.0 (51) +/- 10%	
	Adhesive	0.9-1.0 (23-25) +/- 0.1 (3)	
	Liner	6.8 (172) +/- 10%	
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)	
<b>Adhesion Properties</b>			
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)	
	Oz/In (N/m)		
	Acrylic		55 (605)
	Glass		44 (484)
	Polyethylene		14 (154)
	Polypropylene		31 (341)
	Stainless Steel		46 (506)
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load	
Room Temp (hours)	5		
Tack (gm/sq cm)	620	ASTM D 2979	
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 302°F (-40°C to 150°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Due to the custom nature of this product, the data presented are based on three or less production runs.

**Product Performance and Suitability**

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 02/13/2024

