## Primary and Secondary Labeling Wash-Off Adhesive Label Solution Enabling Recycling of PET Containers

End Use Applications: Rigid Container Labels Semi-Squeeze Container Labels

For Consumable Products including:
Beverages
Food
Health & Beauty
Household Chemical

For more information on FLEXcon's pressure-sensitive film solutions for primary and secondary labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX069992



Product:

Flexcon® OptiFlex® EcoFocus® MPP 200 H Silver TC-458 V-52RE Spec 40K-8

## Benefits:

- Topcoated 1.85 mil hard silver polypropylene (BOPP) offers resistance to shrinkage, moisture, and humidity
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, narrow-format UV inkjet, UV rotary screen, UV letterpress and hot stamping
- V-52RE high-performance adhesive adheres well to PET containers

- V-52RE adhesive separates cleanly from PET flake during the recycling process allowing for the collection of rPET
- 40 lb. bleached white kraft release liner ideal for roll-form converting
- Product has been 3rd party tested for Higher Pressure Processing (HPP) and adhesive was found to have the necessary strength and compatibility to withstand the HPP conditions

APR Critical Guidance Recognition - Flexcon's undecorated OptiFlex® EcoFocus® MPP 200 H Silver TC pressure-sensitive labels, with V-52RE adhesive meet or exceed APR's Critical Guidance Protocol for Clear PET Articles with Labels and Closures



## Flexcon® OptiFlex® EcoFocus® MPP 200 H Silver TC-458 V-52RE Spec 40K-8

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	1.85 (47) +/- 10%	ASTM D 3652 (Modified for use with
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)	non-tape products)
	Liner	2.5 (64) +/- 10%	
Dimensional Stability (%)	MD	0.5	Applied Shrinkage: 24 hour dwell
	TD	0.5	time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour
	Oz/In	(N/m) dwell time)	dwell time)
Polyester	15	(165)	
Stainless Steel	16	(176)	
Expected Shear			ASTM D 3654 Method A
			a. 1 hr. dwell b. 1 sq. in. surface
			c. 4 lb. load
Room Temp (hours)	10		
Tack (gm/sq cm)	500		ASTM D 2979
Expected Exterior Life	Indoor use only		
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)		
Minimum Application Temperature	20°F (-6.6°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50%		

relative humidity

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 05/14/2024

