

Secondary Labeling

Clear Polypropylene with Removable Adhesive

*Get the No-Label-Look Required
for Your Application*

*End-Use Applications
Rigid Container Labels
Semi-Squeeze Container Labels*

*For Consumable Products
including:
Cosmetics
Household Product Labeling*

*For more information on
FLEXcon's
pressure-sensitive film
solutions for Secondary
Container Labeling, contact
your local Sales
Representative or our
Product Branding Business
Team at (508) 885-8370.*

Product ID #: FLX070146



Product:

**Flexcon®
OptiFlex® PP 200 H Clear
TC-458 V-611 Spec 40K-8**

Benefits:

- Topcoated 2.0 mil hard clear polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film clarity is ideal for achieving the no-label-look
- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, UV inkjet (Xeikon Jetrion 4000 series and Domino), UV screen, UV letterpress, and hot stamping
- General-purpose removable adhesive provides minimal adhesion bond over time ensuring clean removability
- Adheres to a wide range of container types
- Adhesive complies with FDA 175.105 for indirect food contact
- Backed with a 40 lb. bleached kraft release liner ideal for roll-form converting
- Order custom widths without purchasing a whole master through [Flexcon® FlexChoice™ for Prime Label](#)

Flexcon®

OptiFlex® PP 200 H Clear

TC-458 V-611 Spec 40K-8

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	2.0 (51) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)	
	Liner	2.5 (64) +/- 10%	
Dimensional Stability (%)	MD	0.5	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	TD	0.5	
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In	(N/m)	
	Aluminum	23 (253)	
	Glass	14 (154)	
	Polyethylene	6 (66)	
	Polypropylene	14 (154)	
	Stainless Steel	17 (187)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	100		
Tack (gm/sq cm)	290		ASTM D 2979
Expected Exterior Life	Indoor use only		
Service Temperature Range	-20°F to 212°F (-29°C to 100°C)		
Minimum Application Temperature	40°F (4°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 04/10/2024

