# Petroleum / Chemical Drum Labeling

White Vinyl - BS 5609

For the Labeling of Steel, Plastic and Fiber Drums

Compliant with the Globally Harmonized System (GHS) of Classification and Labeling of Chemicals

For more information on FLEXcon's pressure-sensitive film solutions for Drum Labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX030593



Product:

## Flexcon® DrumCal™ V 310 F White V-224 74 RB

### Benefits:

- 3.1 mil flexible white vinyl provides excellent chemical resistance for drum labeling applications
- The internal strength of the film facilitates removal during reconditioning
- Excellent printability via most conventional ink systems (for laser printing, a press applied varnish is recommended)
- Adhesive system is designed to bond well to painted steel, fiber and plastic drums
- Product can be applied at low temperatures

- High peel, high shear adhesive resists cold flow and oozing, gaining efficiencies in diecutting and dispensing
- 74 lb. clay-coated release liner possesses excellent lay-flat properties
- Liner tracks well through laser printers and provides an excellent die-cutting base
- Designed for sheet-fed and roll-form laser printers
- 2 year outdoor durability
- BS 5609 compliant



### Flexcon® DrumCal™ V 310 F White V-224 74 RB

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film	3.1 (79) +/- 10%	ASTM D 3652 (Modified for use with
	Adhesive	1.0-1.1 (25-28) +/- 0.1 (3)	non-tape products)
	Liner	6.0 (152) +/- 10%	
Dimensional Stability (%)	MD	0.75	Applied Shrinkage: 24 hour dwell
	TD	0.77	time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour
	Oz/In	(N/m)	dwell time)
Acrylic	93	(1023)	
Glass	74	(814)	
Polypropylene	69	(759)	
Stainless Steel	76	(836)	
Expected Shear			ASTM D 3654 Method A
			a. 1 hr. dwell
			b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	5		
Tack (gm/sq cm)	930		ASTM D 2979
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)		
Minimum Application Temperature	32°F (0°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 10/21/2024

