Consumer Durables

White Polypropylene - Roll Form

End Use Applications:
Compliance Labels
Warning & Instructional Labels
Nameplates
Brand Identity Labels
Markets including:
Appliance
Automotive
Heavy/Outdoor Equipment
Industrial/Manufacturing
Power Equipment

For more information on FLEXcon's pressure-sensitive film solutions for Consumer Durables and more, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX069253



Product:

Flexcon® FlexMark® PP 230 H White TC-458 L-01 120 Poly H-9

Benefits:

- 2.3 mil hard white polypropylene provides consistent surface smoothness and excellent dimensional stability
- Print-receptive surface is printable via flexographic, UV offset, gravure, UV screen, UV letterpress, thermal transfer, narrow-format UV inkjet, and hot stamping
- High-performance acrylic adhesive adheres well to a variety of surfaces

- Backed with an ultra smooth polyester release liner for excellent adhesive wet out
- Release liner provides a good diecutting base
- UL recognized under UL 969 UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component



Flexcon® FlexMark® PP 230 H White TC-458 L-01 120 Poly H-9

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	Film Adhesive Liner	2.3 (58) +/- 10% 0.5-0.6 (13-15) +/- 0.1 (3) 1.2 (30) +/- 5%	ASTM D 3652 (Modified for use with non-tape products)
Dimensional Stability (%)	No Shrinkage Observed		Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average Oz/In	(N/m)	ASTM D 903 (Modified for 72 hour dwell time)
Acrylic	52	(572)	,
Acrylic Glass		• •	
	40	(440)	
Polypropylene	20	(220)	
Stainless Steel	54	(594)	
Expected Shear			ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Room Temp (hours)	10		
Tack (gm/sq cm)	730		ASTM D 2979
Expected Exterior Life	Indoor use only		
Service Temperature Range	-40°F to 212°F (-40°C to 100°C)		
Minimum Application Temperature	35°F (1.7°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50%		

relative humidity

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 10/23/2024

