

Primary and Secondary Labeling

White Polypropylene

*End Use Applications:
Rigid Container Labels
Semi-Squeeze Container Labels*

*For Consumable Products
including:
Beverages
Food
Health & Beauty
Household Chemical*

*For more information on
FLEXcon's
pressure-sensitive film
solutions for primary and
secondary labeling, contact
your local Sales
Representative or our
Product Identification
Business Team at (508)
885-8300.*

Product ID #: FLX000159



Product:

**Flexcon®
OptiFlex® PP 230 H White
TC-332™ V-81 TracRite™ 120**

Benefits:

- 2.3 mil hard white polypropylene offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film conformability for rigid containers provides maximum label and graphic coverage
- Excellent surface smoothness allows for optimum ink laydown
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping
- Flexcon® TracRite™ 120 polyester release liner provides excellent on-press performance for tight-registration graphics, a good diecutting base and allows for high-speed dispensing

Flexcon®

OptiFlex® PP 230 H White

TC-332™ V-81 TracRite™ 120

PRODUCT DATA	VALUE	TEST METHOD		
Physical Properties				
Thickness (Mils[microns])	Film	2.3 (58) +/- 10%		
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)		
	Liner	1.2 (30) +/- 5%		
Dimensional Stability (%)	No Shrinkage Observed	Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)		
Adhesion Properties				
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)		
	Oz/in		(N/m)	
	Acrylic		46	(506)
	Glass		47	(517)
	Polypropylene		10	(110)
Stainless Steel	53	(583)		
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load		
Room Temp (hours)	15			
Tack (gm/sq cm)	710	ASTM D 2979		
Expected Exterior Life	Indoor use only			
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)			
Minimum Application Temperature	50°F (10°F)			
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity			

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.

Last Modified On: 10/28/2024

