Security / Authenticity Labeling

Silver Polyester - Void Pattern

For Tamper-Evident Labeling including: Consumer Electronics or anywhere tamper evidence may be required.

Flexcon makes a variety of destructible and selectively destructible films for covert security applications.

For more information on FLEXcon's pressure-sensitive film solutions for security / authenticity labeling, contact your local Sales Representative or our Product Identification Business Team at (508) 885-8300.

Product ID #: FLX006999



Product:

Flexcon® CompuCal II® TamperMark™ MM 200 Silver VOID MTC-329 L-156 Spec 50K/Q-8

Benefits:

- Matte topcoated 2.0 mil silver matte polyester provides consistent surface smoothness, excellent dimensional stability, and endurance to varying temperatures
- Printable via UV and solvent screen, UV and water flexo, UV and oil offset, UV letterpress, wax/resin & wax thermal transfer, dry toner, and laser
- Designed for applications requiring tamper evidence

*Quilon® is a registered trademark of Zaclon, LLC.

- High-performance, aggressive permanent acrylic adhesive provides a permanent bond to a wide range of surfaces, including powder coated paint and metal
- Backed with a 50 lb. semi-bleached kraft release liner that is Quilon®* coated to prevent label pick-off



Flexcon® CompuCal II® TamperMark™ MM 200 Silver VOID MTC-329 L-156 Spec 50K/Q-8

PRODUCT DATA	VALUE		TEST METHOD
Physical Properties			
Thickness (Mils[microns])	MTC & Film	2.5 (64) +/- 10%	ASTM D 3652 (Modified for use with
	Adhesive	1.0-1.1 (25-28) +/- 0.1 (3)	non-tape products)
	Liner	3.1 (79) +/- 10%	
Dimensional Stability (%)	No Shrinkage Observed		Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
Adhesion Properties			
Ultimate Peel from	Average		ASTM D 903 (Modified for 72 hour
	Oz/In	(N/m)	dwell time)
Acrylic	See footnote	See footnote	
Glass	See footnote	See footnote	
Stainless Steel	See footnote	See footnote	
Expected Shear			ASTM D 3654 Method A
			a. 1 hr. dwell b. 1 sq. in. surface
			c. 4 lb. load
Room Temp (hours)	5		
Tack (gm/sq cm)	880		ASTM D 2979
Expected Exterior Life	Two years		
Service Temperature Range	-40°F to 302°F (-40°C to 150°C) Tamper-evident maximum 104°F (40°C)		
Minimum Application Temperature	32°F (0°C)		
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity		

Product shows tampering when removal is attempted by leaving a "VOID" pattern on the application surface.

Product Performance and Suitability All of the descriptive information, the typical performance data, and recommendations for the use of Flexcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by Flexcon. All purchasers of Flexcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of Flexcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above. Last Modified On: 03/17/2025

